

DataMatrix metal code bars for positioning safePXV and safePGV read heads

Function

Rugged Data Matrix metal code bars made of anodized aluminum for use on the ground in camera-based track guidance. Depending on the application, the code bars can be glued directly to the floor, or glued into special carrier profile rails. The code bars are available in modular lengths of 100, 200, and 500 mm.

Dimensions



Technical Data

Code bar segment	m 76 m
Start position 87 Code bar segment	
Code bar segment	76 m
-	
Nominal segment length 50	
	00 mm
Width 30	0 mm
Ambient conditions	
Operating temperature -4	10 80 °C (-40 176 °F)
Installation temperature 10	0 40 °C (50 104 °F)
	V radiation umidity
Gr Fu Ali	ils rease uels liphatic solvents /eak acids
Mechanical specifications	
Material thickness 1 r	mm
Material Ali	luminum
Mounting type ad	dhesive
Mass 83	3 g / m

Refer to "General Notes Relating to Pepperl+Fuchs Product Information"

Pepperl+Fuchs Group www.pepperl-fuchs.com USA: +1 330 486 0001 fa-info@us.pepperl-fuchs.com Germany: +49 621 776 1111 fa-info@de.pepperl-fuchs.com Singapore: +65 6779 9091 fa-info@sg.pepperl-fuchs.com



Metal code bar

Technical Data

Manufacturing tolerance

± 1 mm/m

Mounting

Preparing the Base Surface

- 1. Use clean cleaning cloths (free from lint and plasticizers) to clean the surfaces.
- 2. Use cleaning agents appropriate for the level of surface contamination, for example n-Heptane, ethanol, or a 50:50 mixture of isopropanol and water.
- 3. Clean the surface until it is completely dry and free of dust, oil, oxides, release agents, and other contaminants.

4. Ensure that the surface is dry, clean, and stable.

Adhesive Strength

Metal	Material with high-energy surfaces	Material with low-energy surfaces
33 N/25 mm	32 N/25 mm	31 N/25 mm

Material thickness: 1 mm code bar + 0.13 mm adhesive

Processing Instructions

During bonding, the pressure should be as high as possible, and the temperature should be at least +10 °C. The higher the pressure and temperature, the better the adhesive will penetrate the pores of the base surface. This allows higher adhesive strength values to be achieved. It takes approx. 72 hours for the adhesive to cure.

Type Code

Structure of the type code

_			-			-		-	-	-						-		-	-		-		-			-		
	Ρ	Х	V	(1)	(1)	(1)	(1)	(1)	(1)	Μ	-	Α	Α	М	(2)	(3)	(3)	х	(4)	(4)	(4)	-	(5)	(5)	(5)	(5)	(5)	(5)

PXV	Sensor Type
PXV	Position Extended Vision
(1) (1) (1) (1) (1) (1)	Total length of the code bar
1 100.000	The total length of the code bar is determined by the number of individual code bar segments. The code bars can be ordered in 1 m units.
М	Unit
М	Meter
AAM	Code bar
A	Code type ECC200, symbol size 16x16
A	Absolute code
Μ	Metall
(2)	Mounting Type
G	Mounting by self-adhesive back
Н	Mounted by screwing or riveting
(3) (3)	Code Bar Width
30	Width of the code bar in mm for mounting type G
50	Width of the code bar in mm for mounting type H
(4) (4) (4)	Nominal segment length of the code bars
100	Nominal segment length of the individual code bars in mm
200	Nominal segment lengthof the individual code bars in mm
500	Nominal segment lengthof the individual code bars in mm
(5) (5) (5) (5) (5) (5)	Start position
1 99.999	Start position of the code bars in m

Refer to "General Notes Relating to Pepperl+Fuchs Product Information"